



EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA
PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16

FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



BARNIAQUA – 692

SPECIAL ANTI-SLIDING AQUEOUS FINISH FOR WOOD FLOOR IN INDOOR SPORTS FACILITIES

PRODUCT DESCRIPTION:

- **DEFINITION:** It is a mono-component based on Aromatic Urethane-acrylic copolymers in aqueous dispersion. The dry film provides a film with excellent chemical resistance and abrasion resistant to friction, etc.
- **USE:** Particularly suitable for Indoor Sports Facilities, Fitness, and large areas of parquet floor.
- **PROPERTIES:** Non toxic, not flammable, it not gives off odor, great strength and hardness.

TECHNICAL INFORMATION

Aspect.....	BRIGHT 94% Lange 60°
Another aspect.....	SATIN and MATTE
Color.....	COLORLESS
P.H.....	8,5 ± 0,2
Viscosity.....	23" FORD CUP N° 4 to 20° C
Volume solids.....	33 - 35%
Theoretical performance.....	8 – 10 M ² /Lt.
Drying 20 °C/70% RH	
Touch.....	2 hours
Overall.....	2 - 3 hours
Repaint.....	7 days

APPLICATION INSTRUCTIONS:

- **Method**
Brush or Roller.
- **Dilution**
If necessary use WATER.
- **Cleaning**
After use, clean all equipment and tools with cold water.
- **Application**
Apply 2 or 3 coats.

SURFACES PREPARATION:

- The surface to be varnished should be clean and free of dust. The temperature at the time of applying the varnish should not be less than 13 ° C. The best use for its application will be with roller and in its absence brush. In a new wood apply a FONDIAQUA-555 layer, and after passing 3 hours at 20 ° C, sand with 240-280 grain sandpaper and then apply 2 or 3 coats of BARNIAQUA-692, leaving 2 or 3 hours of drying between layer and layer.
- This type of coating does not reach its maximum hardness until past 7 days, is not advisable to place mats and other weights or subject it to heavy traffic, up within one week. However, you can carefully step past 2 days from your application. Due to its large adhesion BARNIAQUA-692 is recommended as a varnish restoration for sports floor, whenever the surface to varnishing is clean and free of waxes and similar products, always recommended sanding the surface with 240-280 grain sandpaper.

HYGIENE AND SECURITY:

- Should shake the product before use.
- Product not flammable. No toxic. It not gives off odor.
- Avoid prolonged inhalation of solvent vapors.
- Store in a cool place to avoid both the cold and the excessive heat.
- Avoid contact with skin and eyes, if product comes in contact with skin, wash with soap and water.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 – 562.84.69.

Comments

- * When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- * The solvent addition proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- * Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover. In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.