



EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA
PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16

FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



ACUASO - 724

PRODUCT DESCRIPTION:

- **DEFINITION:** This is specially developed to combat humidity patches.
- **USE:** It is suitable for failure occurred in facades, failures occurred in roofs, etc.
- **PROPERTIES:** Its effectiveness in these cases is excellent; to even can combat, but only temporarily, the capillary humidity.

TECHNICAL INFORMATION

| | |
|------------------------------|--|
| Aspect..... | MATTE |
| Color | WHITE OR ANOTHER ACC/ORDER |
| Density..... | 1.57 +/- 0.05 Kg/Lt. |
| Viscosity..... | 170" – 190" C.F. 4 to 20° C |
| Volume solids..... | 43.6 +/- 0.05 % |
| Solids by weight | 72 +/- 0.05 % |
| Theoretical performance..... | 22 M ² /Lt. or 3.49 M ² /Lt. |
| Recommended thickness..... | 125 MICRONS |
| DRY/FILM | |
| Lifetime mix | 4-6 HOURS |
| Drying 20 °C/70% RH | |
| Touch..... | 1 HOURS |
| Overall | 5 HOURS |
| Repaint | 24 HOURS |
| Storage..... | 1 YEAR |
| "Q" Value..... | 119% |

APPLICATION INSTRUCTIONS:

- **Method**
Brush, Roller, Airbrush gun or Air-Less.
- **Dilution**
If necessary use our D-320 solvent.
- **Cleaning**
After use, clean all equipment with our S.G. Solvent.

SURFACES PREPARATION:

- The surface must be clean of dust, grease or other contamination. In case of old paint is recommended light sanding, and make a quick test first.
- It is recommended for best adhesion, slightly wetting the surface with a sponge, this promotes the adhesion and the initiation of the anti-humidity reaction. In case of patch it is recommended to apply 15 cm. more around the spot moisture.

HYGIENE AND SECURITY:

- Being a flammable product, keep away from sparks and flames.
- It is recommended the most appropriate respiratory protection to each case by the corresponding mask.
- Avoid prolonged inhalation of solvent vapors.
- During the application have adequate ventilation and maintain a constant air renewal.
- Avoid eye and skin contact, if product comes in contact with skin, wash with soap and water.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 – 562.84.69.

Comments

- * When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- * The solvent addition proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- * Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.