



# EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959  
POLÍGONO DE SALCEDO - 33120 PRAVIA  
PRINCIPADO DE ASTURIAS (ESPAÑA)  
TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16  
FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS  
E-mail: eupines@terra.es



## SANDSTONE SEALANT A - 222

### PRODUCT DESCRIPTION:

- **DEFINITION:** Sealant made from acrylic emulsions with a very fine particle size which allows sealing surfaces even in low porosity.
- **USE:** Can be used as sealant primer for both indoors and outdoors to later apply all kinds of plastic paints. Also as a protective and finishing varnish over surfaces such as stone and brick.
- **PROPERTIES:** Can waterproof porous surfaces, which carries a lower consumption of paint on finish coatings. The plaster and sand that fall off with just a touch, once sealed with this product is firmly affixed.

### TECHNICAL INFORMATION

Aspect..... SATIN  
 Color..... COLORLESS  
 Density..... 1 Kg/Lt.  
 Minimum temperature application. 7° C  
 Theoretical performance..... 10 M<sup>2</sup>/Kg.  
 Drying 20 °C/70% RH  
 Touch..... 1 - 2 HOURS  
 Repaint..... 4 - 6 HOURS  
 Storage..... 1 YEAR

### APPLICATION INSTRUCTIONS:

- **Method**  
Brush, Roller, Airbrush gun.
- **Dilution**  
If necessary use only water.
- **Cleaning**  
After use, clean all equipment with water, preferably hot.

### SURFACES PREPARATION:

- On new surfaces is applied directly with a dilution of 1/1 to 1/3 depending on the porosity degree.
- In old surfaces after removal of soft parts by scratching, apply a layer of this sealant diluted 1/1 to 1/2 in water and with it will avoid all kinds of detachments of temper, lime, sand, plaster, etc.

### HYGIENE AND SECURITY:

- Non-flammable product.
- Because contain no toxic product, no precautions are necessary in this regard.
- If applied by spray mask is recommended.
- It should not apply in very cold weather where there are temperatures below or close to 0° C.
- Preserves the paint can of frost.

### Comments

- \* When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- \* The solvent addiction proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- \* Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.