



EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA
PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16
FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



H - 200

PRODUCT DESCRIPTION:

- **DEFINITION:** Anticorrosive primer pigmented with zinc phosphate, synthetic type and quick drying.
- **USE:** As antioxidant for steel surfaces, structural profiles, machinery, equipment and boiler-room in rural or industrial environment highly aggressive.
- **PROPERTIES:** As an anticorrosive protection. It has very good covering, speed of drying and hardening.

TECHNICAL INFORMATION

Aspect.....	MATTE
Color.....	RED RUST, OLIVE GREEN
Density.....	1.23 ± 0.05
Viscosity.....	110 – 120" FORD
Volume solids.....	36% ± 2
Recommended thickness.....	40 micron
Theoretical performance.....	9 M ² /Lt
Max. Continuous Temp.	100°C
Drying 20 °C/70% RH	
Touch.....	30 minutes
Overall.....	6hours
Repaint.....	8 hours

APPLICATION INSTRUCTIONS:

- **Method**
Brush, Roller, Airbrush gun, Air-Less
- **Dilution**
If necessary use our Solvent S. G.
- **Cleaning**
After use, clean all equipment with our solvent S. G.

SURFACES PREPARATION:

We recommend a cleaning with a sandblasting or shot through grade 2 ½. If this is not possible, manual cleaning should remove all traces of rust and calamine.

HYGIENE AND SECURITY:

- Being a flammable product, keep away from sparks and flames.
- It is recommended the most appropriate respiratory protection to each case by the corresponding mask.
- Avoid prolonged inhalation of solvent vapors.
- During the application have adequate ventilation and maintain a constant air renewal.
- Avoid eye and skin contact, if product comes in contact with skin, wash with soap and water.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 – 562.84.69.

Comments

- * When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- * The solvent addition proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- * Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.