



# EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA  
PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16

FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



## IMPRITERMI – W – 666

### PRIMER FINISH

#### PRODUCT DESCRIPTION:

- **DEFINITION:** It is a fast drying synthetic paint that performs anticorrosive functions at once as primer and high solidity to light and bad weather as synthetic enamel.
- **USE:** As a layer of finish in any industrial paint process and as protection of elements outlined in marine, rural and industrial environment.
- **PROPERTIES:** Its high quality gives excellent anticorrosive properties, as well as outdoors and indoors resistance, presents very good surface leveling and very fast drying.

#### TECHNICAL INFORMATION

Aspect.....	GLOSS or SATIN
Color.....	ACC/ RAL CHART
Density.....	1,3 Kg/Lt.
Viscosity.....	70 - 80 K.U. a 25°C
Volume solids.....	48%
Recommended thickness.....	40 micron
Theoretical performance.....	12 M <sup>2</sup> /Lt.
Drying 20 °C/70% RH	
Touch.....	20 MINUTES
Overall.....	3 hours
Repaint.....	12 hours

#### APPLICATION INSTRUCTIONS:

- **Method**  
Brush, Roller, Airbrush gun, Air-Less
- **Dilution**  
If necessary use our Solvent D-302.
- **Cleaning**  
After use, clean all equipment with our Solvent S.G.

#### SURFACES PREPARATION:

The surface to be treated should be clean of dust and grease. It is recommended abrasive blasting to grade Sa<sup>1/2</sup> of the Swedish standard SIS 055900; in case it is not possible to reach this surface preparation grade, has to do a good mechanical cleaning.

#### HYGIENE AND SECURITY:

- Being a flammable product, keep away from sparks and flames.
- It is recommended the most appropriate respiratory protection to each case by the corresponding mask.
- Avoid prolonged inhalation of solvent vapors.
- During the application have adequate ventilation and maintain a constant air renewal.
- Avoid eye and skin contact, if product comes in contact with skin, wash with soap and water.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 – 562.84.69.

#### Comments

- \* When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- \* The solvent addiction proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- \* Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.