



EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA
PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16
FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



P.M.A. – 24

ANTICORROSIVE METALLIC PAINT

PRODUCT DESCRIPTION:

- **DEFINITION:** It is an antioxidant metallic paint, thixotropic, pigmented with micaceous iron oxide.
- **USE:** It is used as an excellent protective of bars, railings, doors, street lamps, metal structures, bridges, walkways, etc.
- **PROPERTIES:** It is ideally designed to protect and beautify the iron surfaces with a new metallic look forging type.

TECHNICAL INFORMATION

Aspect..... MATTE
 Color..... Acc. forge chart
 Density..... 1,70 - 1,85 Kg/Lt.
 Volume solids..... 51%
 Recommended thickness..... 80 micron
 Theoretical performance..... 6,4 M²/Lt.
 Drying 20 °C/70% RH
 Touch..... 30 MINUTES
 Overall..... 4 hours
 Repaint..... 24 hours

APPLICATION INSTRUCTIONS:

- **Method**
Brush, Roller and Airbrush gun.
- **Dilution**
If necessary use our Solvent D - 307.
- **Cleaning**
After use, clean all equipment with our Solvent S. G.

SURFACES PREPARATION:

Remove oxide, calamine, grease, etc., using a barbed iron brush and then wash with S. G. solvent. Then apply one coat of our zinc phosphate Lymuse. Past 24 hours apply two layers of P.M.A. – 24 with an interval of 24 hours between both layers.

HYGIENE AND SECURITY:

- R10 Flammable.
- R65 Harmful if swallowed may cause lung damage.
- S2 Keep out of reach of children.
- S24 Avoid contact with skin.
- S43 In case of fire, use water spray, anti-alcohol foam, dry chemical powder, carbon anhydride.
- S51 Use only in well ventilated areas.
- S36/37/39 Wear protective clothing, gloves and eye protection.

Hazardous Ingredients: None in a percentage equal to or above to man.

Comments

- * When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- * The solvent addition proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- * Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.