



# EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA  
PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16  
FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



## REFLET 27 E

### PRODUCT DESCRIPTION:

- **DEFINITION:** Fluorescent and reflective paint of high adhesion and resistance, both indoors and outdoors.
- **USE:** Is particularly suitable for signals in any location where there is no good illumination.
- **PROPERTIES:** Great hardness, flexibility and adhesion on supports of metal, wood, concrete, etc.

### TECHNICAL INFORMATION

Aspect.....	BRIGHT
Color.....	Shades on chart RAL F3
Density.....	1,2 Kg/Lt.
Viscosity.....	65 – 75 K. U.
Volume solids.....	51%
Recommended thickness.....	35 - 40 micron
Theoretical performance.....	10 - 12M <sup>2</sup> /Lt.
Drying 20 °C/70% RH	
Touch.....	1 hour
Overall.....	24 hours

### APPLICATION INSTRUCTIONS:

- **Method**  
Brush, Roller, Airbrush gun, Air-Less
- **Dilution**  
If necessary use our Solvent Reflet-27-E.
- **Cleaning**  
After use, clean all equipment with our Solvent S. G.

### DIRECTIONS:

On any type of surface, clean, dry, degreased and if metal, properly primed, apply one or two good layers of REFLET – 27 – E. Five minutes later, and always on wet paint, apply MICROSPHERES 3-F, with machine or sprinkling by hand from about 20 cm high, in order that half of each MICROSPHERE is sufficiently embedded on the paint film. Let the treatment dry during 24 hours prior to subjecting the surface to use.

Should never be mixed MICROSPHERES 3-F with the painting inside the can nor paint over the MICROSPHERES.  
Do not use any solvent in such treatment unless it is a porous support.

### HYGIENE AND SECURITY:

- Being a flammable product, keep away from sparks and flames.
- It is recommended the most appropriate respiratory protection to each case by the corresponding mask.
- Avoid prolonged inhalation of solvent vapors.
- During the application have adequate ventilation and maintain a constant air renewal.
- Avoid eye and skin contact, if product comes in contact with skin, wash with soap and water.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 – 562.84.69.

### Comments

- \* When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- \* The solvent addiction proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- \* Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.