



EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA
PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16

FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



ALBAYATEL

SPECIAL PROTECTOR JOINT COVER

PRODUCT DESCRIPTION:

- **DEFINITION:** Coating based on rubber liquid and a combination of thixotropic synthetic resins.
- **USE:** As a waterproofing leak protector in a thick layer for concrete, mortar, cement, asbestos cement, steel, etc.
- **PROPERTIES:** Resistant to high temperature and all types of industrial environments.

TECHNICAL INFORMATION

Volume solids.....	68% ± 1%
Viscosity.....	THIXOTROPIC
Aspect.....	SATIN
Color.....	INDUSTRIAL GRAY
Specific Weight	2.48 ± 1%
Minimum Temperature Application....	Above 10 ° C
Theoretical performance.....	0,68 M ² /Lt.
Continuous Thermal Resistance:.....	200 ° C
"Q" VALUE.....	111.74%.
Recommended thickness.....	1 mm to 2 mm

APPLICATION INSTRUCTIONS:

- **Method**
Short hair brush, Roller, Airbrush gun, Spatula.
- **Dilution**
If necessary use only our ALBAYATEL diluents.
- **Cleaning**
After use, clean all equipment with our ALBAYATEL diluents.
- **Storage**
One year minimum temperatures 5 ° C and maximum 40 ° C.
Original container unopened.

SURFACES PREPARATION:

- The surface must be clean of all contamination such as grease, oil, dust, etc. The first coat can be a bit diluted by 5% to 10%. The following as supplied until achieve the desired thickness and finish.
- The following coats can be applied at intervals of 24 hours and undiluted.

HYGIENE AND SECURITY:

- Keep container out of reach of children.
- Do not empty into drains.
- Dispose of product waste and its container with all possible precautions.
- Use primarily in well ventilated areas.
- In case of accidental ingestion consult your doctor or the National Institute of Toxicology Phone: 91.562.84.69/04.20.

Comments

- * When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- * The solvent addiction proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- * Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.