



EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA
PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16

FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



ACRILIC SILICON

PRODUCT DESCRIPTION:

- **DEFINITION:** Silicone-modified coating with acrylic resins.
- **USE:** For the protection of steel parts that have to withstand high temperatures.
- **PROPERTIES:** Thermo resistant. Has excellent waterproofing power. Has very good hardness.

TECHNICAL INFORMATION

Aspect.....SATIN
 Color..... ACC/CHART.
 Density..... 1,3 Kg/Lt.
 Viscosity.....70 – 80 K.U.
 Volume solids..... 36%
 Recommended thickness.....35 micron
 Theoretical performance..... 10,3 M²/Lt.
 Continuous thermal resistance..... 250° C
 Drying 20 °C/70% RH
 Touch..... 1 HOUR
 Overall8 HOURS
 Repaint 24 HOURS

APPLICATION INSTRUCTIONS:

- **Method**
Brush, Roller, Airbrush gun, Air-Less
- **Dilution**
If necessary use our D-307 Solvent.
- **Cleaning**
After use, clean all equipment with our S. G. Solvent.

SURFACES PREPARATION:

The surface to be painted must be completely clean of dust and grease and should be applied on adequate anticorrosive primers.

HYGIENE AND SECURITY:

- Being a flammable product, keep away from sparks and flames.
- It is recommended the most appropriate respiratory protection to each case by the corresponding mask.
- Avoid prolonged inhalation of solvent vapors.
- During the application have adequate ventilation and maintain a constant air renewal.
- Avoid eye and skin contact, if product comes in contact with skin, wash with soap and water.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 – 562.84.69.

Comments

- * When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- * The solvent addition proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- * Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.