



EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959
 POLÍGONO DE SALCEDO - 33120 PRAVIA
 PRINCIPADO DE ASTURIAS (ESPAÑA)
 TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16
 FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS
 E-mail: eupines@terra.es



SS – 200 C

PRODUCT DESCRIPTION:

- **DEFINITION:** Painting made from thermoset polymers and pigmented only with type "Leafing" aluminum sheet and resistant to constant temperature of 200 ° C.
- **USE:** On exposed metal parts on a temporary or permanent way to moderately elevated temperatures such as chimneys, steam pipes, furnaces, heating boilers and industrial autoclaves.
- **PROPERTIES:** Provides a good chemical stability film, as well as good resistance to scrub and humidity.

TECHNICAL INFORMATION

Aspect..... BRIGHT
 Color..... ALUMINUM GRAY
 Density..... 1,01 Kg/Lt.
 Viscosity..... 52" FORD CUP N° 4.
 Volume solids..... 28%
 Recommended thickness..... 30 - 35 micron
 Theoretical performance..... 8 - 9 M²/Lt.
 Drying 20 °C/70% RH
 Touch..... 35 MINUTES
 Overall 2 HOURS
 Repaint 24 HOURS

APPLICATION INSTRUCTIONS:

- **Method**
Brush, Roller, Airbrush gun, Air-Less
- **Dilution**
If necessary use our D – 300 Solvent.
- **Cleaning**
After use, clean all equipment with our Solvent S. G.

SURFACES PREPARATION:

Preparation is made by cleaning the surface to be treated through sandblasting until grade 2 S ½ of the Swedish Standard SIS 055900. When not possible, deep cleaning by mechanical or manual and subsequent degreasing with solvent.

HYGIENE AND SECURITY:

- Being a flammable product, keep away from sparks and flames.
- It is recommended the most appropriate respiratory protection to each case by the corresponding mask.
- Avoid prolonged inhalation of solvent vapors.
- During the application have adequate ventilation and maintain a constant air renewal.
- Avoid eye and skin contact, if product comes in contact with skin, wash with soap and water.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 – 562.84.69.

Comments

- * When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- * The solvent addition proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- * Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.
 In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.