



EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA
PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16
FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



BARNIFLAT - INDOORS

PRODUCT DESCRIPTION:

- **DEFINITION:** Colorless varnish made from synthetic-base resins.
- **USE:** For protection, decoration and beautification of all sorts of indoor wood
- **PROPERTIES:** Excellent hardness and elasticity.

TECHNICAL INFORMATION

Aspect.....	BRIGHT, SATIN AND MATTE
Color.....	COLORLESS
Density.....	0,9 Kg/Lt.
Viscosity.....	100" Ford cup -4 to 20° C
Volume solids.....	48%
Recommended thickness.....	46 micron
Theoretical performance.....	15,3 M ² /Lt.
Drying 20 °C/70% RH	
Touch.....	3 hours
Overall.....	10 hours
Repaint.....	24 hours

APPLICATION INSTRUCTIONS:

- **Method**
Brush, Roller, and Airbrush gun.
- **Dilution**
For airbrush gun application can be diluted up to 10% with our D-300 Solvent.
- **Cleaning**
After use, clean all equipment with our S.G. Solvent.

SURFACES PREPARATION:

- On new dry wood, apply one or two coats of Nitrocellulose Lacquer Sealer and after a light sanding will be applied two coats of **BARNIFLAT INDOORS**.
- On already varnished wood it has to remove the loose debris and traces of dirt.
- To get a good finish it is necessary to keep the environment free of dust during application and drying.

HYGIENE AND SECURITY:

- Being a flammable product, keep away from sparks and flames.
- It is recommended the most appropriate respiratory protection to each case by the corresponding mask.
- Avoid prolonged inhalation of solvent vapors.
- During the application have adequate ventilation and maintain a constant air renewal.
- Avoid eye and skin contact, if product comes in contact with skin, wash with soap and water.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 – 562.84.69.

Comment

- * When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- * The solvent addiction proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- * Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.