



EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA
PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16

FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



ESCLOR - 500

FINISHING CHLORINATED RUBBER ENAMEL

PRODUCT DESCRIPTION:

- **DEFINITION:** Finish paint made based on chlorinated rubber resins and high quality pigments. It fulfills SSPC-SP-19 standard.
- **USE:** As a topcoat in chlorinated rubber systems painting, for the metallic structures treatment subjected to industrial or marine environments. Also used for concrete surfaces protection.
- **PROPERTIES:** Very fast physical drying. It has high resistance to water and chemicals.

TECHNICAL INFORMATION

Aspect.....	SEMIGLOSS
Color.....	ACC/CHART.
Density.....	1.1 – 1.25 Kg/Lt.
Viscosity.....	70 - 80 K.U.
Volume solids.....	40%
Recommended thickness.....	35 - 40 micron
Theoretical performance.....	9.5 M ² /Lt.
Drying 20 °C/70% RH	
Touch.....	30 MINUTES
Overall	2 HOURS
Repaint	ONCE DRIED

APPLICATION INSTRUCTIONS:

- **Method**
Brush, Roller, Airbrush gun, Air-Less.
- **Dilution**
If necessary use our D - 307 Solvent.
- **Cleaning**
After use, clean all equipment with our S. G. Solvent.

SURFACES PREPARATION:

- Metal surfaces: to apply on anticorrosive primer or intermediate adequate layers, for high or low thickness.
- Concrete: removes all kinds of pounce or dust and on the dry surface will be applied a first-coat diluted to 10% and a finishing second coat.

HYGIENE AND SECURITY:

- Being a flammable product, keep away from sparks and flames.
- It is recommended the most appropriate respiratory protection to each case by the corresponding mask.
- Avoid prolonged inhalation of solvent vapors.
- During the application have adequate ventilation and maintain a constant air renewal.
- Avoid eye and skin contact, if product comes in contact with skin, wash with soap and water.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 – 562.84.69.

Comment

- * When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- * The solvent addition proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- * Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover. In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.