



EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA
PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16

FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



IMPAL – 379 - C

ALKYD ANTICORROSION PRIMER WITH THICK CHLORINATED RUBBER

PRODUCT DESCRIPTION:

- **DEFINITION:** Painting made with alkyd resins to the chlorinated rubber, designed for applications as ideal workshop primer, on which we recommend to finish with synthetic enamels, alkyds or chlorinated rubber.
- **USE:** As barrier layer in alkyds-chlorinated rubber systems for steel protection in industrial environments.
- **PROPERTIES:** Good chemical resistance, special fast drying. High thickness, since thixotropic thickness is easily obtained. It has great performance.

TECHNICAL INFORMATION

Aspect.....	SEMIGLOSS
Color.....	WHITE, GRAY AND RED.
Density.....	1.52 Kg/Lt.
Viscosity.....	90 - 110 K.U.
Volume solids.....	50.2%
Recommended thickness.....	100 micron
Theoretical performance.....	5 M ² /Lt.
Drying 20 °C/70% RH	
Touch.....	14 MINUTES
Overall	1 HOURS
Repaint	6 HOURS
Q VALUE.....	68.05%

APPLICATION INSTRUCTIONS:

- **Method**
Brush, Roller, Airbrush gun, Air-Less.
- **Dilution**
If necessary use our D - 307 Solvent.
- **Cleaning**
After use, clean all equipment with our Solvent S. G.

SURFACES PREPARATION:

In rural, industrial or domestic environment, manual or mechanical preparation is sufficient.

If the surface is highly oxidized and the environment is aggressive, we recommend a cleaning grade Sa 2 ½.

HYGIENE AND SECURITY:

- Being a flammable product, keep away from sparks and flames.
- It is recommended the most appropriate respiratory protection to each case by the corresponding mask.
- Avoid prolonged inhalation of solvent vapors.
- During the application have adequate ventilation and maintain a constant air renewal.
- Avoid eye and skin contact, if product comes in contact with skin, wash with soap and water.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 – 562.84.69.

Comment

- * When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- * The solvent addiction proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- * Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.