



EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959
POLÍGONO DE SALCEDO - 33120 PRAVIA
PRINCIPADO DE ASTURIAS (ESPAÑA)
TELÉF.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16
FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS
E-mail: eupines@terra.es



TABLE OF RESISTANCE TO FIRE AND EFFICIENCY OF TIX EUROFIRE-870

FIRE RESISTANCE ACC UNE-23,093 POLICY	PAINT SYSTEMS	THICKNESS (MICRONS)	NUMBER OF LAYERS			CONSUMPTION Kg./M ²
			ROLLER	BRUSH	AIR-LESS	
RF-30 FIRE RESISTANCE 30 MINUTES	LYMUSE-125, ZINC PHOSPHATE PRIMER OR RX-24	30	1	1	1	0,175
	EUROFIRE-870 TIX	400	2	2	1	0,340
	ESCLOR-VARNISH	30	1	1	1	0,150
RF-60 FIRE RESISTANCE 60 MINUTES	LYMUSE-125, ZINC PHOSPHATE PRIMER OR RX-24	30	1	1	1	0,175
	EUROFIRE-870 TIX	1200	3	3	2	2,520
	ESCLOR-VARNISH	30	1	1	1	0,150
RF-90 FIRE RESISTANCE 90 MINUTES	LYMUSE-125, ZINC PHOSPHATE PRIMER OR RX-24	30	1	1	1	0,175
	EUROFIRE-870 TIX	1800	4	4	3	3,780
	ESCLOR-VARNISH	30	1	1	1	0,150
RF-120 FIRE RESISTANCE 120 MINUTES	LYMUSE-125, ZINC PHOSPHATE PRIMER OR RX-24	30	1	1	1	0,175
	EUROFIRE-870 TIX	2200	5	4	4	4,200
	ESCLOR-VARNISH	30	1	1	1	0,150
RF-180 FIRE RESISTANCE 180 MINUTES	LYMUSE-125, ZINC PHOSPHATE PRIMER OR RX-24	30	1	1	1	0,175
	EUROFIRE-870 TIX	3600	9	9	6	7,560
	ESCLOR-VARNISH	30	1	1	1	0,150

NOTE: THERE ARE TWO TREATMENTS, ONE BY WATER AND ANOTHER BY SOLVENT, TO EACH CASE PLEASE CONTACT US.

THE NUMBER OF LAYERS AND YIELDS ARE ESTIMATED AT ORIENTATIVE LEVEL AS DEPENDS ON APPLICATOR AND USED SYSTEM.