



EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA
PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16

FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



FONDEUROEPOX – SK 2/C SPECIAL SEALER FOR EPOXY TYPE FLOOR.

PRODUCT DESCRIPTION:

- **DEFINITION:** Two-component sealant Epoxy type made to achieve good adhesion for the subsequent epoxies or polyurethanes application coatings.
- **USE:** Particularly suitable for treating any type of floor as a sealer after cleaning dust, grease, oil, etc. It also serves as a treatment of anti-dusting.
- **PROPERTIES:** Excellent chemical resistance to solvents, water and alkali. It can be repainting both with finished epoxy type. Acts as a bond bridge to the subsequent implementation of subsequent products.

TECHNICAL INFORMATION

Aspect.....	BRIGHT
Color.....	COLORLESS
Density.....	0.912 +/- 0.05 Kg/Lt.
Volume solids.....	7.14 %
Proportion and lifetime mixing.....	2/1 VOL. / 6 - 8 HOURS
Recommended thickness.....	15 MICRONS
Theoretical performance.....	4,75 M ² /Lt.
Drying 20 °C/70% RH	
Touch.....	20 MINUTES
Overall	7 HOURS
Repaint	MIN. 6 H. MAX. 7 DAYS

APPLICATION INSTRUCTIONS:

- **Method**
Brush, Roller, Airbrush gun, Air-Less
- **Dilution**
If necessary use our Epoxy - A Solvent.
- **Cleaning**
After use, clean all equipment with our Epoxy - A Solvent.
- **Storage**
Under cover for 12 months with an ambient temperature and frost free.

SURFACES PREPARATION:

The surface must be free of dust, grease, oil, and any type of contamination, especially if the floor is polished with wax or grease.

HYGIENE AND SECURITY:

- R10 Flammable.
- R20/21 Harmful by inhalation and skin contact.
- R36/37/38 Irritating to eyes, skin and respiratory tract.
- S23 Do not breathe vapors or aerosols.
- S38 In case of insufficient ventilation, use suitable respiratory equipment.
- S43 In case of fire, anti-alcohol foam, dry chemical powder, carbon dioxide, AFFF.
- S36/37 Use protective and suitable clothing and gloves.
Hazardous components: Xylene (mixed isomers) and polyamide.

Comments

- * When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- * The solvent addition proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- * Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.