



# EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959  
POLÍGONO DE SALCEDO - 33120 PRAVIA  
PRINCIPADO DE ASTURIAS (ESPAÑA)  
TELÉF.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16  
FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS  
E-mail: eupines@terra.es



## TERMIPOX 801

### PRODUCT DESCRIPTION:

- **DEFINITION:** Two-component coating type Epoxy-Polyamide, reinforced with micaceous iron oxide, formulated to achieve high dry film thicknesses.
- **USE:** As an intermediate layer for steel treatment in marine and industrial applications.
- **PROPERTIES:** Excellent chemical resistance to solvents, water and alkali. It has high film thickness. It can be repainting with both epoxy and polyurethane type finishes and high degree of impermeability.

### TECHNICAL INFORMATION

Aspect.....	SILK
Color.....	GRAY
Density.....	1,45 Kg/Lt
Viscosity.....	85 – 100 K. U.
Volume solids.....	63 %
Proportion / lifetime mixing.....	3/1 VOL. / 6 - 8 HOURS
Recommended thickness.....	80 - 100 MICRONS
Theoretical performance.....	4,8 - 6 M <sup>2</sup> /Lt
Drying 20 °C/70% RH	
Touch.....	2 HOURS
Overall .....	7 HOURS
Repaint .....	3 HOURS

### APPLICATION INSTRUCTIONS:

- **Method**  
Brush, Roller, Airbrush gun, Air-Less
- **Dilution**  
If necessary use our Epoxy Solvent.
- **Cleaning**  
After use, clean all equipment with our Epoxy Solvent.

### SURFACES PREPARATION:

It should be applied to appropriate and anticorrosive primer and the surface to be treated must be completely clean of dust and grease.

### HYGIENE AND SECURITY:

- Being a flammable product, keep away from sparks and flames.
- It is recommended the most appropriate respiratory protection to each case by the corresponding mask.
- Avoid prolonged inhalation of solvent vapors.
- During the application have adequate ventilation and maintain a constant air renewal.
- Avoid eye and skin contact, if product comes in contact with skin, wash with soap and water.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 – 562.84.69.

### Comments

- \* When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- \* The solvent addition proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- \* Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.