



# EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959  
POLÍGONO DE SALCEDO - 33120 PRAVIA  
PRINCIPADO DE ASTURIAS (ESPAÑA)  
TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16  
FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS  
E-mail: eupines@terra.es



## JOMARCRYL

### THERMOPLASTIC ACRYLIC PAINT

#### PRODUCT DESCRIPTION:

- **DEFINITION:** Painting made based on special thermoplastic acrylic resins and synthetic resins mix.
- **USE:** For external surface protection for all types of metal structures properly primed. In marine and industrial environments of medium and high alkalinity, acid and aggressive environments, etc.
- **PROPERTIES:** Hard surface, waterproof and anti-dusting. It can be applied to temperature below freezing. It has stable brightness, powerful anticorrosive and strong adhesion.

#### TECHNICAL INFORMATION

Aspect.....	SATIN, BRIGHTH
Color.....	ALL RAL CHART F3
Density.....	1,40 Kg/Lt.
Viscosity.....	65 – 75 K.U.
Volume solids.....	40 %
Recommended thickness.....	50 MICRONS
Theoretical performance.....	7 M <sup>2</sup> /Lt.
Drying 20 °C/70% RH	
Touch.....	30 MINUTES
Overall .....	24 HOURS
Repaint .....	48 HOURS

#### APPLICATION INSTRUCTIONS:

- **Method**  
Brush, Roller, Airbrush gun or Air-Less.
- **Dilution**  
If necessary use our D-308 solvent.
- **Cleaning**  
After use, clean all equipment with our S.G. Solvent.
- **Storage**  
One year.

#### SURFACES PREPARATION:

**IRON AND STEEL:** In a rural and industrial environment, manual or mechanical preparation will be enough. If the surface is highly oxidized is recommended a sand blasting to grade Sa2. In both cases, apply the proper primer before proceeding to apply JOMARCRYL.

**NON-FERROUS METALS:** For aluminum, stainless steel, galvanized steel and other non-ferrous metals should be used special treatments. Before applying JOMARCRYL apply the most appropriate primer for each case.

#### HYGIENE AND SECURITY:

- Being a flammable product, keep away from sparks and flames.
- It is recommended the most appropriate respiratory protection to each case by the corresponding mask.
- Avoid prolonged inhalation of solvent vapors.
- During the application have adequate ventilation and maintain a constant air renewal.
- Avoid eye and skin contact, if product comes in contact with skin, wash with soap and water.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 – 562.84.69.

#### Comments

- \* When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- \* The solvent addition proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- \* Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.