



EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA
PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16

FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



SELLEPOX 100% S. V.

PRODUCT DESCRIPTION:

- **DEFINITION:** Is a product of EPOXY Nature. Its use is as solvent free sealer coat, high penetrating power in all sorts of surfaces, compatible with all types of old paintings that are obviously well-anchored, accepts all types of finishes, compatible with substrates with even high humidity (80-90% R.H.). Its use for marine, in particular for hulls protection, is to make sure to have no adhesive failures between the old and new paint products (sealing).
- **USE:** After degreasing and rinsing with fresh water at high pressure, we get the best results in all substrates penetrability due to its high moisturizing power.
- **PROPERTIES:** Excellent performance as it must be applied very low microns (38 microns), 100% solids by volume, meets all the IMO regulations, provides to the system an excellent environment anticorrosion protection.

TECHNICAL INFORMATION

Aspect.....	GLOSS	
Color	CLEAR	
Volume solids.....	100 %	
Recommended thickness.....	38 MICRONS	
Theoretical performance.....	27.1 M ² /Lt.	
Proportion mix.....	3 - 1 VOLUME	
Lifetime mix	4-6 HOURS	
Drying (hours)	21°C	10°C
Touch.....	10.....	16
Handling.....	16.....	24
Repaint (hours)	21°C	10°C
Minimum.....	12.....	20
Maximum.....	72.....	72

APPLICATION INSTRUCTIONS:

- **Method**
Brush, Roller, Airbrush gun or Air-Less.
- **Dilution**
NO.
- **Cleaning**
After use, clean all equipment with our Epoxy Solvent.

SURFACES PREPARATION:

ONLY: Beware of Dust, Grease and Contaminants and the paintings on which it will be applied are well attached.

HYGIENE AND SECURITY:

- Being a flammable product, keep away from sparks and flames.
- It is recommended the most appropriate respiratory protection to each case by the corresponding mask.
- During the application have adequate ventilation and maintain a constant air renewal.
- Avoid eye and skin contact, if product comes in contact with skin, wash with soap and water.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 – 562.84.69.

Comments

- * When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- * The solvent addition proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- * Our Technical Department will be pleased to answer as many as questions that you are planning to ask.
- * JorgeMarino@telecable.es Naval Director, Shop Primer, Metallization, Anticorrosive Protection and Industrial Maintenance.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.