

# ANTI DUST P - 14

#### **PRODUCT DESCRIPTION:**

DEFINITION: Polyurethane painting of two components particularly suitable for concrete and cement floors treatment, facade and interior and exterior walls acting as self-cleaning and anti dust.
USE: As termination layer in high wear floors and resistance to weather, abrasion, moisture, aggressive

As termination layer in high wear floors and resistance to weather, abrasion, moisture, aggressive environments, oil spills, solvents, acids, alkalis and pallet truck traffic.

#### **TECHNICAL INFORMATION**

Aspect	GLOSS
Color	TRANSPARENT and
	RAL
Mix proportion	4/1
Density	$1 \pm 0.05$
Viscosity	35" ± 2 FORD CUP 4
Volume solids	37 %
Recommended thickness	35 MICRONS
Theoretical performance	10 to 11 M <sup>2</sup> /Lt.
Drying 20 °C/70% RH	
Touch	3 HOURS
Overall	4 HOURS

## APPLICATION INSTRUCTIONS:

- **Method** Brush, Roller, Airbrush gun, Air-Less.
- **Dilution** If necessary use our Polyurethane Solvent.
- Cleaning After use, clean all equipment with our S.G. Solvent.

# SURFACES PREPARATION:

- \* Sweep and vacuum the floor well, removing dirt, grease and being the floor completely dry. Then mix and stir well both components for 5 minutes to reach its full homogenization.
- <sup>\*</sup> Then apply a good coat of ANTI DUST P-14 diluted in the range of 5 to 10%.
- \* Past 2 hours, apply a second coat of ANTI DUST P-14 as it is and let it dry for 48 hours before use.

### **HYGIENE AND SECURITY:**

- Being a flammable product, keep away from sparks and flames.
- It is recommended the most appropriate respiratory protection to each case by the corresponding mask.
- Avoid prolonged inhalation of solvent vapors.
- During the application have adequate ventilation and maintain a constant air renewal.
- Avoid eye and skin contact, if product comes in contact with skin, wash with soap and water.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 – 562.84.69.

### Comments

- \* When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- \* The solvent addiction proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- \* Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.