



# EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA  
PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16

FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



## GALVA – POLY 91/MDC. 2/C ENAMEL POLYURETHANE FINISH FOR GALVANIZED.

### PRODUCT DESCRIPTION:

- **DEFINITION:** Aliphatic Polyurethane paint of 2/C for galvanized surfaces.
- **USE:** Coating for all types of galvanized, whether cold or hot as single painting.
- **PROPERTIES:** Excellent adhesion on any galvanized substrate for interior and exterior, with good weather resistance without loss of brightness and color.  
If necessary it can be applied directly on iron completely oxide free, thanks to its high antioxidant power.

### TECHNICAL INFORMATION

Aspect.....	GLOSS, SATIN, MATTE
Color.....	RAL 9002 and ACC/ORDER
Density.....	1.4 +/- 0.05 Kg/Lt.. ACC/COLOR
Volume solids.....	46 % MIN.
Recommended thickness.....	60 MICRONS
Mix proportion.....	9/1 BY WEIGHT and 6/1 BY VOLUME
Lifetime mix.....	12 HOURS MIN.
Theoretical performance.....	5.4 M <sup>2</sup> /Kg and 7.7 M <sup>2</sup> /Lt..
Drying 20 °C/70% RH	
Touch.....	20 minutes at 20° C
Overall.....	6 hours at 20° C
Repaint.....	12 hours at 20° C
Q value.....	62.5 % ACC/COLOR

### APPLICATION INSTRUCTIONS:

- **Method**  
Brush, Roller, Airbrush gun, Air-Less.
- **Dilution**  
If necessary use our Galvapoly Solvent.
- **Cleaning**  
After use, clean all equipment with our S.G. Solvent.
- **Storage**  
At Cover for 1 year at room temperature without freezing.

### SURFACES PREPARATION:

The surface must be completely free of grease, oil, dust or other contamination.

### HYGIENE AND SECURITY:

- R10 Flammable.
- R34 Causes burns.
- R38 Irritating to skin.
- R65 Harmful: if swallowed may cause lung damage.
- S3 Keep in a cool place.
- S23 Do not breathe vapors or aerosols.
- S38 In case of insufficient ventilation, use suitable respiratory equipment.
- S24/25 Avoid contact with eyes and skin.
- P91 Contains isocyanates. See information supplied by the manufacturer.
- Hazardous components: None in equal or exceeding percentage to the limit for the name.

### Comments

- \* When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- \* The solvent addition proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- \* Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.