



EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA
PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16
FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



IMPULGAL AC - 500

PRODUCT DESCRIPTION:

- **DEFINITION:** Antioxidant Primer of 2-component, polyurethane based for galvanized, steel, aluminum, etc., surfaces.
- **USE:** Anticorrosive coating for galvanized surfaces, whether hot or cold, or other metals such as steel, aluminum, etc.
- **PROPERTIES:** Great antioxidant power, and excellent adhesion, as bottom for any type of finish (polyurethane, epoxy synthetic, etc.)

TECHNICAL INFORMATION

Aspect.....	SATIN, MATTE
Color.....	WHITE or ANOTHERS ACC/ORDER
Density.....	1.33 +/- 0.05 Kg/Lt.
Volume solids.....	42 % MIN.
Recommended thickness.....	25 MICRONS MIN.
Theoretical performance.....	16.8 M ² /Lt.
Drying 20 °C/70% RH	
Touch.....	11 MINUTES
Overall.....	1 HOUR
Repaint.....	12 HOURS
Mix proportion.....	4/1 BY VOLUME or 11/2 BY WEIGHT
Q value.....	57 % (WHITE)

APPLICATION INSTRUCTIONS:

- **Method**
Brush, Roller, Airbrush gun.
- **Dilution**
Use our Polyurethane Solvent.
- **Cleaning**
Use our S.G. cleaning solvent.
- **Storage**
At covered for 1 year at room temperature and without open the package.

SURFACES PREPARATION:

The surface must be completely free of grease, oil, oxides, dust or other contamination.

HYGIENE AND SECURITY:

- Flammable.
- Harmful by inhalation and skin contact.
- Irritating to skin.
- May cause sensitization by inhalation.
- Keep away from flames, sources of ignition ... No smoking.
- Do not breathe vapors.
- Avoid contact with eyes and skin.
- Contains isocyanates. Taking into account manufacturer's instruction.

Comments

- * When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- * The solvent addition proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- * Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.