



# EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA  
PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16

FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



## AUTOBAJ – THICK LAYER

### PRODUCT DESCRIPTION:

- **DEFINITION:** It is a mastic asphalt of cold application.
- **USE:** As soundproof paint in automotive bottom, as well as in steel structures, getting the insulation of it in very thick layers.
- **PROPERTIES:** It can achieve very high layer thicknesses due to presenting a thixotropic aspect for asphalt composition and mineral based on needle-shaped and laminar crystals.

### TECHNICAL INFORMATION

Aspect..... MATTE  
 Color.....BLACK  
 Density..... 1.5 Kg/Lt.  
 Viscosity.....THIXOTROPIC  
 Recommended thickness..... 1 – 1.5 MILIMETERS  
 Theoretical performance.....0.2 – 0.3 M<sup>2</sup>/Lt.  
 Drying 20 °C/70% RH  
 Touch.....3 - 4 HOURS  
 Continuous maximum temperature 60° C

### APPLICATION INSTRUCTIONS:

- **Method**  
Brush, Roller, Airbrush gun, Air-Less.
- **Dilution**  
If necessary use our S.G. Solvent.
- **Cleaning**  
After use, clean all equipment with our S.G. Solvent.

### SURFACES PREPARATION:

- \* Surfaces must be dry and free of dust and grease.
- \* The best results are obtained if a surface preparation is made by sandblasting.

### HYGIENE AND SECURITY:

- Non-flammable product.
- Because contain no toxic product, no precautions are necessary in this regard.
- If applied by spray mask is recommended.
- It should not apply in very cold weather where there are temperatures below or close to 0 ° C.
- Preserves the paint can of frost.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 – 562.84.69.

### Comments

- \* When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- \* The solvent addition proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- \* Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.