



EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA
PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16
FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



H - 25 2/C POLYESTER PUTTY

PRODUCT DESCRIPTION:

- **DEFINITION:** Polyester Putty of two components, catalyzed with di-benzoyl peroxide.
- **USE:** In any kind of work which requires plugging or filling gaps of some importance. It can work as sheet leveler in car body work, shipbuilding, etc.
- **PROPERTIES:** Moldable in a pasty state, high hardness, good expansion, easy to polish and paint, etc.

TECHNICAL INFORMATION

Aspect..... SEMI - MATTE
 Color.....GRAY
 Density..... 2.48 Kg/Lt
 Recommended thickness..... ACC CASES
 Theoretical performance..... THICKNESS TO 50
 MICRONS = 1.5 M²/1.5
 Kg.
 Drying 20 °C/70% RH
 Touch..... 15 MINUTES
 Overall.....1.5 HOURS
 Repaint..... 3 HOURS
 Sand.....30 MINUTES

APPLICATION INSTRUCTIONS:

- **Method**
On a steel spatula COMBINE component "A" with "B" (peroxide) in the amount indicated in the can and as needed. If we put more catalyst (peroxide) it can get better drying, more hardness and less flexibility.
- **Cleaning**
After use, clean all equipment with our S.G. Solvent.

SURFACES PREPARATION:

IRON and STEEL: The surface must be clean, dry and degreased prior to application of H-25 2 / C.

HYGIENE AND SECURITY:

- Being a flammable product, that irritates the eyes; keep away from sparks and flames.
- It is recommended the most appropriate respiratory protection to each case by the corresponding mask.
- Avoid prolonged inhalation of solvent vapors.
- During the application have adequate ventilation and maintain a constant air renewal.
- Avoid eye and skin contact, if product comes in contact with skin, wash with soap and water.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 - 562.84.69.

Comments

- * When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- * The solvent addition proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- * Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.
 In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.