



EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA
PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16
FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



EUROELECTRIC 2/C - 3000

PRODUCT DESCRIPTION:

- **DEFINITION:** Special product highly anti-corrosive and electrically conductive of two-components with anti-caloric properties up to 120° C continuously.
- **USE:** As anti-corrosive treatment for iron and steel treatment it has to be applied two coats of Euroelectric-3000, until pass the 130 micron dry film.
- **PROPERTIES:** Anti-corrosive protection of galvanic type. It has high resistance to weathering, abrasion, to caustic soda solutions, water vapor, etc.

TECHNICAL INFORMATION

Aspect.....	SILK
Color.....	GRAY
Density.....	2,45 Kg/Lt.
Ratio/mix life.....	10/2 VOL. / 8 HOURS
Viscosity.....	THIXOTROPIC
Volume solid.....	58 %
Recommended thickness.....	60 – 70 MICRON
Theoretical performance.....	11,6 M ² /Lt.
Alternating thermal resistance.....	150° C
Continuous thermal resistance.....	120° C
Average dielectric conductivity	26 KV/CM
Drying 20 °C/70% RH	
Touch.....	30 MINUTES
Overall.....	16 HOURS
Repaint.....	MIN. 6 HOURS MAX. without limits

APPLICATION INSTRUCTIONS:

- **Method**
Brush, Roller, Airbrush gun, Air-Less.
- **Dilution**
If it's necessary, had to be used **EUROELECTRIC-3000 solvent** in proportions ranging from 5 to 10% depending on the application method to be used.
- **Cleaning**
After use, clean all equipment with our W - 300 Solvent.

SURFACES PREPARATION:

To get good protection it is essential to clean by sandblasting to grade SA 2 ½ of Swedish Standard SIS 055900 and then apply the 2-3 coatings of EUROELECTRIC-3000.

HYGIENE AND SECURITY:

- Being a flammable product, keep away from sparks and flames.
- It is recommended the most appropriate respiratory protection to each case by the corresponding mask.
- Avoid prolonged inhalation of solvent vapors.
- During the application have adequate ventilation and maintain a constant air renewal.
- Avoid eye and skin contact, if product comes in contact with skin, wash with soap and water.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 – 562.84.69.

Comments

- * When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- * The solvent addiction proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- * Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.