



EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA
PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16
FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



MARTEL ENAMEL

PRODUCT DESCRIPTION:

- **DEFINITION:** Special paint with a hammered look finish with which the decorative characteristic aspects are achieved due to the appearance of small craters distributed evenly on the paint film.
- **USE:** As a finish coat on all types of industrial machinery, steel tools, boxes and metal cabinets.
- **PROPERTIES:** Highly resistant to rubbing and impact, been its finish very hard. Because of these special effects obtained, it hides very well faults of the pieces to paint.

TECHNICAL INFORMATION

Aspect.....	BRIGHT MARTEL
Color.....	ACC/CHART
Density.....	0,96 Kg/Lt.
Viscosity.....	50" FORD CUP N° 4
Volume solids.....	39 %
Recommended thickness.....	30 MICRAS
Theoretical performance.....	13 M ² /Lt.
Type.....	SILICONE HIGH EYE
Drying 20 °C/70% RH	
Touch.....	30 MINUTES
Overall.....	3 HOURS

APPLICATION INSTRUCTIONS:

- **Method**
Brush, Roller, Airbrush gun, Air-Less.
- **Dilution**
If necessary use our S.G. Solvent.
- **Cleaning**
After use, clean all equipment with our S.G. Solvent.

SURFACES PREPARATION:

Hammered enamel can be applied directly on iron or steel, either blasting or perfectly clean and degreased. When greater protections of the pieces are desired, it is recommend a first coat of ANTICORROSIVE PRIMER as our LYMUSE-125.

HYGIENE AND SECURITY:

- Being a flammable product, keep away from sparks and flames.
- It is recommended the most appropriate respiratory protection to each case by the corresponding mask.
- Avoid prolonged inhalation of solvent vapors.
- During the application have adequate ventilation and maintain a constant air renewal.
- Avoid eye and skin contact, if product comes in contact with skin, wash with soap and water.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 – 562.84.69.

Comments

- * When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- * The solvent addiction proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- * Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.