



# EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA  
PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16  
FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



## F - 25

### PRODUCT DESCRIPTION:

- **DEFINITION:** Waterproofing sealant for facades composed by acrylic resins on solvent.
- **USE:** It can be applied primarily on the following surfaces and treatments:
  - Plastering mortar
  - All kinds of stucco
  - Joints where there is leakage
  - Normal and Bare brickwork
  - Plastic paints, lime and tempera
  - Mold produced in dairies industries
  - Artificial and natural stone.
  - Avoid humidity stains.
  - Hardener and accelerator of wet or dead plaster.
  - Concrete facings
  - Not saponizable
  - Concrete floors
  - Wood
  - Revives the stone
- **PROPERTIES:** It has a high resistance to weathering. Once dry, has good hardness and is an ideal product to enhance stone burdens of any kind.

### TECHNICAL INFORMATION

Aspect..... SEMI-GLOSS  
 Liquid color.....COLORLESS  
 Interval between layers..... 4 HOURS  
 Viscosity..... 14" FORD CUP N° 4  
 Volume solids..... 19 % ± 2 %  
 Recommended thickness.....20 – 25 MICRONS  
 Specific weight.....0.900 ± 2 %  
 Max. temperature resistance..... 70° C  
 Adhesion..... 100 %  
 Toxicity once dry..... ATOX  
 Average performance..... 6 – 7 M²/Lt  
 Adequate solvent..... D - 307  
 Drying 20 °C/70% RH  
 Touch.....30 MINUTES  
 Repaint..... 12 HOURS

### APPLICATION INSTRUCTIONS:

- **Method**  
Apply the first coat diluted to 10% and a second coat as supplied, i.e. without dilution. In all cases must be made with wool roller or brush. In special cases can be applied by immersion and spray guns with nozzle 1 to 1,5 mm. and pressure of 3 to 4 atmospheres.
- **Process**  
For each case, should be requested the treatment to seek. Before each application, must homogenize the container contents, stirring it.
- **Cleaning**  
After use, clean all equipment with our D – 307 Solvent.

### SURFACES PREPARATION:

All surfaces must be previously cleaned of dust and dirt, dried and degreased; for these we recommend use our **Humidity Degreaser-Sequestrate S.G.** When used as a finish it should be applied two coats. When used as a sealer is enough one coat diluted to 10%. In case of old paint existence, in poor condition, lack of grip, etc., proceed to eliminate it before applying the F-25. If the paints were old and were in good condition, but there were several layers, is preferable to remove it before applying the F-25 in order to avoid possible detachment in some layer. Over F-25 can be applied all types of water paints, chlorinated rubber, synthetic and grease.

### HYGIENE AND SECURITY:

- Being a flammable product, keep away from sparks and flames.
- It is recommended the most appropriate respiratory protection to each case by the corresponding mask.
- Avoid prolonged inhalation of solvent vapors.
- During the application have adequate ventilation and maintain a constant air renewal.
- Avoid eye and skin contact, if product comes in contact with skin, wash with soap and water.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 – 562.84.69.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.