



# EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA  
PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16  
FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



## VITREN - 230

### PRODUCT DESCRIPTION:

- **DEFINITION:** It is an elastic special anti-mold and vitrifier of stone surfaces and polyurethane based. It is a product very suitable for waterproofing and makes washable lots of surfaces.
- **USE:** It can be applied primarily on the following surfaces and treatments:
  - Plastering mortar
  - Normal and Bare brickwork
  - Artificial and natural stone.
  - Concrete facings
  - Wood
  - All kinds of stucco
  - Plastic paints, lime and tempera
  - Avoid humidity stains.
  - Not saponizable
  - Revives the stone
  - Joints where there is leakage
  - Mold produced in dairies industries
  - Hardener and accelerator of wet or dead plaster.
  - Concrete floors
- **PROPERTIES:** Excellent weather resistance without brightness loss. Once dry, it has high resistance to grease and oils.

### TECHNICAL INFORMATION

Aspect.....	GLOSS
Color.....	COLORLESS
Stability to ultraviolet rays.....	TOTAL
Viscosity.....	15" FORD CUP N° 4
Volume solids.....	21 % ± 2 %
Recommended thickness.....	30 – 40 MICRONS
Specific weight.....	0.955 ± 2 %
Max. temperature resistance.....	100° C
Adhesion.....	100 %
Toxicity once dry.....	ATOX
Average performance.....	10 – 12 M <sup>2</sup> /Lt.
Adequate solvent.....	D - 307
Drying 20 °C/70% RH	
Touch.....	3 HOURS
Repaint.....	12 - 24 HOURS

### APPLICATION INSTRUCTIONS:

- **Method**  
In all cases must be made with wool roller or brush. In special cases it can be applied by immersion and spray guns with nozzle 1 to 1,5 mm and pressure of 3 to 4 atmospheres.
- **Dilution**  
Remove the contents of the can always to a metal container never of plastic. In exterior or highly resistant processes it must be applied three coats of finish. For each case, please ask us the treatment to follow.
- **Cleaning**  
After use, clean all equipment with our T – 140 Solvent.

### SURFACES PREPARATION:

All surfaces must be previously cleaned, dried and degreased; for these we recommend use our S.G. HUMIDITY SEQUESTANT DEGREASER.

### HYGIENE AND SECURITY:

- Being a flammable product, keep away from sparks and flames.
- It is recommended the most appropriate respiratory protection to each case by the corresponding mask.
- Avoid prolonged inhalation of solvent vapors.
- During the application have adequate ventilation and maintain a constant air renewal.
- Avoid eye and skin contact, if product comes in contact with skin, wash with soap and water.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 – 562.84.69.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.