



# EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA  
PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16

FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



## WASH – PRIMER 2/C POLYVINYL BUTYRAL PHOSPHATE PRIMER

### PRODUCT DESCRIPTION:

- **DEFINITION:** Priming of two components prepared based on polyvinyl butyral resins and an acid catalyst, carrying anti-corrosive pigments in its formulation.
- **USE:** For galvanized steel treatment, stainless steel, aluminum and all types of light alloys and metalized surfaces, where it can get a perfect anchorage and be able to subsequently do a repaint with any type of system.
- **PROPERTIES:** Dries very fast and has excellent anchorage on all types of metal bracket.

### TECHNICAL INFORMATION

Aspect.....	MATT
Color.....	YELLOWISH
Density.....	0.9 Kg/Lt.
Viscosity.....	55 – 60 K.U.
Volume solids.....	10 %
Proportion mix.....	4/1 (by volume)
Recommended thickness.....	8 MICRONS
Theoretical performance.....	12,5 M <sup>2</sup> /Lt.
Drying 20 °C/70% RH	
Touch.....	5 MINUTES
Overall.....	30 MINUTES
Repaint.....	6 HOURS

### APPLICATION INSTRUCTIONS:

- **Method**  
Brush, Roller, Airbrush gun, Air-Less.
- **Dilution**  
Dilute between 5 and 10% with Wash-Primer Solvent.
- **Pot life**  
12 HOURS
- **Cleaning**  
After use, clean all equipment with our S.G. Solvent.

### Surfaces preparation:

It is applied directly onto the surface to be treated, which must be clean of dust and degreased.

### HYGIENE AND SECURITY:

- Being a flammable product, keep away from sparks and flames.
- It is recommended the most appropriate respiratory protection to each case by the corresponding mask.
- Avoid prolonged inhalation of solvent vapors.
- During the application have adequate ventilation and maintain a constant air renewal.
- Avoid eye and skin contact, if product comes in contact with skin, wash with soap and water.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 – 562.84.69.

### Comments

- \* When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- \* The solvent addition proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- \* Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.