



EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA
PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16
FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



W. S. H. - 27

PRODUCT DESCRIPTION:

- **DEFINITION:** Anti cryptogrammic vinyl paint satin appearance with which it can be achieved an excellent behavior in continuous immersion in water.
- **USE:** It is used as protection for pools, cistern, water tanks, etc., in both rural and industrial environments.
- **PROPERTIES:** High resistance to water, alkalis and diluted acids. It has high solidity to light and weather. It has great anti-mold and fungicide power.

TECHNICAL INFORMATION

Aspect.....	SATIN
Color.....	WHITE AND COLORS
Density.....	1.3 Kg/Lt.
Viscosity.....	120" FORD N° 4
Volume solids.....	46 %
Recommended thickness.....	35 MICRONS
Theoretical performance.....	13.1 M ² /Lt.
Drying 20 °C/70% RH	
Touch.....	30 MINUTES
Overall.....	8 HOURS
Repaint.....	24 HOURS

APPLICATION INSTRUCTIONS:

- **Method**
Brush, Roller, Airbrush gun, Air-Less.
- **Dilution**
If necessary use our Vinyl Solvent.
- **Cleaning**
After use, clean all equipment with our S.G. Solvent.

Surfaces preparation:

Clean with detergent, removing all powder and dust residue. Will be applied two consecutive coats, the first painting previously diluted with 10% of our Vinyl solvent and the second coat just as it is supplied. It is recommended to wait 5 to 7 days before filling the pool or water tank.

HYGIENE AND SECURITY:

- Being a flammable product, keep away from sparks and flames.
- It is recommended the most appropriate respiratory protection to each case by the corresponding mask.
- Avoid prolonged inhalation of solvent vapors.
- During the application have adequate ventilation and maintain a constant air renewal.
- Avoid eye and skin contact, if product comes in contact with skin, wash with soap and water.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 – 562.84.69.

Comments

- * When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- * The solvent addition proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- * Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover. In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.